

thortex

www.thortex.co.uk

Telephone: 01609 780170

Facsimile: 01609 780438 & 777905

Facsimile: 01609 788718 (Technical) & 783762 (Sales)

E mail: thortex@ewood.co.uk

Web site: www.thortex.co.uk

Buy online: www.thortex.co.uk/shop

Thortex, Division of E.Wood Ltd, Standard Way, Northallerton, North Yorkshire, DL6 2XA, United Kingdom.

**FDA EXTRACTION TEST RESULTS
IN ACCORDANCE WITH FDA PUBLICATION CFR 21 SECTION 175.300**

ISSUE EW/0304	DISTILLED WATER at 120°F for 24 hrs	8% ETHANOL in distilled water at 120°F 24 hrs	NORMAL HEPTANE at 70°F 30 mins
UNI-TECH GP PRIMER	0.19	0.35	0.18
UNI-TECH MC PRIMER	0.20	0.25	0.18
UNI-TECH UV	0.11	0.21	0.10
WALL-TECH UV	0.29	0.30	0.10
WALL-TECH WB	0.29	0.42	0.18
WALL-TECH LW	0.11	0.19	0.00
FLOOR-TECH SP PRIMER	0.05	0.10	0.00
FLOOR-TECH FBX	0.31	0.46	0.18
FLOOR-TECH WB	0.28	0.46	0.15
FLOOR-TECH WBX	0.25	0.41	0.12
FLOOR-TECH HB	0.07	0.12	0.00
FLOOR-TECH XSL	0.07	0.10	0.00
FLOOR-TECH RS	0.10	0.20	0.00
FLOOR-TECH PR	0.10	0.20	0.00
FLOOR-TECH IS	0.10	0.20	0.00
FLOOR-TECH WS	0.29	0.30	0.10
FLOOR-TECH FB	0.31	0.46	0.18
FLOOR-TECH SFU	0.10	0.20	0.05
FLOOR-TECH PSL	0.31	0.46	0.18
GRANO-TECH	0.08	0.17	0.00
GRIP-TECH	0.07	0.13	0.00
METAL-TECH EG	0.11	0.24	0.00
METAL-TECH FG	0.20	0.33	0.00
METAL-TECH RG	0.18	0.38	0.00
METAL-TECH XG	0.23	0.41	0.00
CERAMI-TECH EG	0.13	0.21	0.00
CERAMI-TECH FG	0.21	0.39	0.00
CERAMI-TECH HG	0.14	0.27	0.00
CERAMI-TECH CR	0.20	0.35	0.00
CERAMI-TECH 88	0.20	0.25	0.18
CERAMI-FLEX EG/FG	0.31	0.46	0.18
CHEMI-TECH CR	0.20	0.33	0.00
CHEMI-TECH PW	0.20	0.35	0.00
CHEMI-TECH PU	0.31	0.46	0.18
CORRO-TECH GP	0.49	0.56	0.31

*In accordance with FDA publication results shown are milligrams extracted per square inch of exposed surface.
Maximum permissible extractives is 18 mgm/sq. inch.*



Registered Office:
Standard Way, Northallerton, North Yorkshire,
DL6 2XA, United Kingdom.
Registration No. 2110605 England

BUILDING MAINTENANCE ●
CORROSION & CHEMICAL PROTECTION ●
ENGINEERING REPAIR & MAINTENANCE ●